

2.B.5 - Carbide Production

Short description

Category Code	Method					AD					EF				
2.B.5	T3					PS					PS				
Key Category	SO ₂	NO _x	NH ₃	NM VOC	CO	BC	Pb	Hg	Cd	Diox	PAH	HCB	TSP	PM ₁₀	PM _{2.5}
2.B.5	-	-	-	-	-	-	-	-	-	-	-	-	-/-	-/-	-/-

T = key source by Trend **L** = key source by Level

Methods	
D	Default
RA	Reference Approach
T1	Tier 1 / Simple Methodology *
T2	Tier 2*
T3	Tier 3 / Detailed Methodology *
C	CORINAIR
CS	Country Specific
M	Model
* as described in the EMEP/CORINAIR Emission Inventory Guidebook - 2007, in the group specific chapters.	
AD - Data Source for Activity Data	
NS	National Statistics
RS	Regional Statistics
IS	International Statistics
PS	Plant Specific data
AS	Associations, business organisations
Q	specific questionnaires, surveys
EF - Emission Factors	
D	Default (EMEP Guidebook)
C	Confidential
CS	Country Specific
PS	Plant Specific data

During the German Reunification period, **calcium carbide** production took place primarily in the new German Länder. A short time later, production there was discontinued and only one producer remained in the old German Länder. In the period under consideration, this producer cut its production by about 50 per cent.

According to the responsible specialised association within the VCI, **no silicon carbide** has been produced in Germany since 1993. Emissions from this sector thus no longer occur.

Method

Activity data

Since Germany has only one producer, the relevant data must be kept confidential. The only published data consists of that for amounts produced in the former GDR. That data was published, until 1989, by that country's central statistical authority. Those figures were used in combination with existing estimates for 1991 and 1992 to interpolate production in the new German Länder in 1990.

Emission factors

In covered furnaces, producers collect all of the carbon monoxide produced in the process and recycle it for further use. Following such use for energy recovery – i.e., following its combustion to produce carbon dioxide – it serves as an auxiliary substance for production of lime nitrogen and secondary products. Reactions in these processes yield carbon dioxide in mineral form, as black chalk. In this form, it is used in agriculture. Upon request, the relevant producer provides the German Environment Agency with data on amounts produced.

The emission factor for TSP is provided by the producer and is also confidential.

Recalculations

Because of a technical mistake, the EF of TSP, PM₁₀ and PM_{2.5} are corrected for the year 2017. TSP-EF is changed from 0.036 to 0.034 kg/t.



For pollutant-specific information on recalculated emission estimates for Base Year and 2018, please see the pollutant specific recalculation tables following [chapter 8.1 - Recalculations](#).

Planned improvements

At the moment, no category-specific improvements are planned.